



TECHNICAL DATA SHEET

Basecoat Plaster (with Fibres)

RJ 2.02

Description:	Non-hydraulic lime putty base-coat plaster produced from 6 month mature Chalk lime putty mixed with washed medium limestone sands at a ratio of 1:2½ by volume. Fibres are added at a rate equivalent to 2½ kgs animal hair per tonne (SPH5). We strongly recommend that SPH7 with additional fibres (equivalent to 3½ kgs animal hair per tonne) is used for the 'pricking-up' coat to ceiling laths.
Environment:	Lime Putty plaster is an environmentally sustainable product.
Uses:	<p>For internal plaster base-coats (dubbing, pricking-up/scratch, and float) where a soft, porous, permeable plaster is appropriate. Base-coat plasters are applied in maximum 10mm thick coats and finished with Fine Finish Plaster (RJ 2.04) and decorated with a permeable paint such as Limewash (RJ 3.01/3.02), or Soft or Casein Distemper (RJ 4.01/RJ4.02).</p> <p>Do not apply Oil-Bound Distemper (RJ 4.03) to new lime plaster.</p>
Availability:	Heat-sealed bags (c.25kgs, 40/tonne); 15 litre tubs (c.28kgs, 36/tonne) Bulk bags (c.1 tonne). Standard mixes are supplied ex Stock.
Shelf Life:	<p>Unlimited. Matures and workability with age. Lime putty plasters stiffen during storage but can be plasticised by thorough re-mixing without the addition of water.</p> <p>Keep in original sealed bags or tubs. Protect from frost.</p>
Coverage (Approx):	Approx 50 m ² /tonne at 10mm thickness
Observations:	Tradesmen familiar with lime putty plaster, and with experience of its successful use should be employed. Lime putty plasters do not perform as gypsum, cement or hydraulic lime plasters and set by carbonation alone (the reaction with atmospheric carbon dioxide in the presence of moisture). This is a slow process and keeping moist by mist-spraying to promote carbonation, 'tending' to prevent shrinkage crazing, and protecting is crucial to success and long-term performance. Protections are essential. Do not use in excessive heat or if risk of frost.

**Health & Safety:**

See Health and Safety Data Sheet RJ 5.02.
CALCIUM HYDROXIDE $\text{Ca}(\text{OH})_2$ Alkali (pH 13).
CAS No 1305-62-0. EINECS No 215-137-3.
Danger: H318 Causes Serious Eye Damage.
Warning: H315 Causes skin irritation.

Technical Data:

TAN 7 Internal Plain Lime Plastering.
TAN 9 Hair/fibre reinforcement in basecoat plasters
RJ 2.09 External Lime Putty Renders.

Technical Advice:

From our Technical Department 01935 83676
info@roseofjericho.co.uk
Product + H & S data can be printed from our web site:
www.roseofjericho.co.uk

Disclaimer:

The information provided in this product data sheet and all technical advice is for guidance and is given in good faith but without warranty, since the site conditions and care and skill of application are beyond our control. We can accept no liability for the performance of our products, beyond the value of the material supplied. This does not affect your statutory rights.